

Formulations of patches

with Nucleophile free base.

with and without 1,2 Propanediol

①

1430 / ²⁶ 38 + 1.2 PD / 15 Sel

without 1.2 PD

	solids	liq	1/5 liq
GMS 1430 (41% sol)	85.0	207.3	69.1
1.2 PD	26.0 0.0	0.0	0.0
Sol free base	113 15.0	15.0	5.0
E+OH	30.0 μ	30.0 μ	10.0

이와
같이
타매

2)

1430 / 35 1.2 PD / 15 Sel

with 1.2 PD

	Solids	1/2	1/3 liq
GMS 1430 (41%)	50.0	121.95	40.7
1.2 PD	35.0	35.0	11.7
Del (free base)	15.0	15.0	5.0
E+OH	20.0	20.0	7.0

To Page No._____

Witnessed & Understood by me,

Date _____

Invent d by

Date ..

Recorded by _____

Liberty

A. Gann

Project No. _____

Book No. 24

TITLE

Formulation (cont)

TITLE

Pec

From Page No. _____

#3

1753 / ~~20~~ 1.2 PD / 15 Sel

without 1.2 PD

	solids	liqu.	1/3 liqu.
Gelva 1753 (28.3%)	85.0	303.6	101.2
1.2 PD	0.0	0.0	0.0
Sol (free base)	15.0	15.0	5.0
EtOH	30.0 _{lv}	30.0 _{lv}	10.0 _{lv}

Sol was mixed with EtOH and added to 1753 while mixing.

#4

1753 / 35 1.2 PD / 15 Sel

	solids	liqu.	1/3 liqu.
Gelva 1753 / 35 1.2 PD / 15 Sel			
Gelva 1753	50.0	171.5 176.75	57.17 58.94
1.2 PD	35.0	35.0	11.7
Sol (free base)	15.0	15.0	5.0
EtOH	20.0	20.0	7.0

EtOH was added to 1753

Sol was mixed with 1.2 PD and added to 1753 while mixing

T Page No. _____

Witnessed & Understood by me,

Date

Invented by

Date

Recorded by

Witnessed & U

Liz Coop